



Influence of $\text{Ni}_x\text{Mn}_{1-x}$ thickness and composition on the Curie temperature of Ni in $\text{Ni}_x\text{Mn}_{1-x}/\text{Ni}$ bilayers on $\text{Cu}_3\text{Au}(001)$



M. Erkovan^{a,*}, Y.A. Shokr^b, D. Schiestl^b, C.-B. Wu^{b,1}, W. Kuch^b

^a Sakarya University, Materials Science and Engineering Department, 54687 Sakarya, Turkey

^b Institut für Experimentalphysik, Freie Universität Berlin, Arnimallee 14, 14195 Berlin, Germany

ARTICLE INFO

Available online 15 February 2014

ABSTRACT

We present a magneto-optical Kerr effect study of epitaxial bilayers consisting of Ni and $\text{Ni}_x\text{Mn}_{1-x}$ on $\text{Cu}_3\text{Au}(001)$. The bottom Ni layer, the $\text{Ni}_x\text{Mn}_{1-x}$ layer thickness and its chemical composition were changed and the Curie temperature of the system was determined. We focused on two different regimes of $\text{Ni}_x\text{Mn}_{1-x}$ composition, namely a Mn-rich with x between 0.25 and 0.5, and a Ni-rich with x around 0.7. In these two composition ranges, a $\text{Ni}_x\text{Mn}_{1-x}$ overlayer exhibits a different effect on the Curie temperature of the Ni layer. While Mn-rich $\text{Ni}_x\text{Mn}_{1-x}$ layers reduce the Curie temperature of the Ni underlayer, Ni-rich $\text{Ni}_x\text{Mn}_{1-x}$ layers enhance the Curie temperature with respect to the pure Ni film. This is attributed to changes in the effective thickness of the Ni layer by exchange interactions with the $\text{Ni}_x\text{Mn}_{1-x}$ overlayer.

© 2014 Elsevier B.V. All rights reserved.

1. Introduction

Antiferromagnetic (AFM) materials are fundamental components for spintronic applications [1]. In particular, they have found wide usage in connection with the exchange bias (EB) effect discovered in the 1950s [2] to define a reference magnetization direction to the ferromagnetic (FM) layer [3]. Spintronic applications are based on the EB effect of various AFM layers such as CoO [4], NiMn [5,6], FeMn [7], IrMn [8], etc. However, technological applications demand some additional properties from AFM materials, such as high blocking temperature, good corrosion resistance, and high exchange-bias fields. NiMn is one of the AFM materials which satisfy these demands [9]. The spin frustration at the interface is a key in determining the overall magnetic properties of FM/AFM systems [3,6,10]. For binary alloy AFM materials like NiMn, this frustration may also depend on the alloy composition. In this study, we have investigated the magnetic properties of epitaxial $\text{Ni}_x\text{Mn}_{1-x}/\text{Ni}$ bilayer film systems in two different concentration regimes of $\text{Ni}_x\text{Mn}_{1-x}$ (x between 0.25 and 0.5, “Mn-rich”, and x around 0.7, “Ni-rich”). We focused on the variation of the Curie temperature T_C of the ferromagnetic Ni layers during the initial stages of deposition of the $\text{Ni}_x\text{Mn}_{1-x}$ overlayer. We find an opposite behavior in the two concentration regimes, pointing towards a strong dependence of interfacial spin frustration on the alloy composition of NiMn.

2. Sample preparation

All experiments were performed in an ultrahigh-vacuum chamber pumped to a base pressure of $< 3 \times 10^{-10}$ mbar. The chamber was designed both for thin film preparation and magnetic characterization. Electron-beam evaporators were used for the deposition of Ni and Mn on a $\text{Cu}_3\text{Au}(001)$ single crystal surface. The $\text{Ni}_x\text{Mn}_{1-x}$ chemical composition x was analyzed by Auger electron spectroscopy (AES). Magnetic hysteresis loops of the samples were taken by in-situ magneto-optical Kerr effect (MOKE) measurements. The growth and structure of ultrathin epitaxial $\text{Ni}_x\text{Mn}_{1-x}$ films on $\text{Cu}_3\text{Au}(001)$ is discussed in another paper [11].

Before growth of the samples, the substrate was cleaned by Ar^+ sputtering (1–2 keV) and annealing at 800 K for 15 min. The sputtering and annealing sequence was repeated until a sharp medium-energy electron diffraction (MEED) image was observed. Ni and $\text{Ni}_x\text{Mn}_{1-x}$ layers were grown by (co-)evaporation from high-purity metal rods (99.999% for Ni, 99.99% for Mn) at room temperature (RT). The film thickness was controlled by in-situ MEED. A typical deposition rate was ~ 1 atomic monolayer (ML)/min. More details can be found in Ref. [5].

3. Results and discussion

Since the purpose of this paper is to study the influence on T_C of $\text{Ni}/\text{Cu}_3\text{Au}(001)$ of a top $\text{Ni}_x\text{Mn}_{1-x}$ layer also for different Ni thicknesses, it is important to first determine the dependence of T_C on the thickness of the Ni layer. T_C can be determined by

* Corresponding author.

E-mail address: merkovan@sakarya.edu.tr (M. Erkovan).

¹ Present address: Chung Yuan Christian University, 200 Chung Pei Road, Chung Li City, Taiwan 32023, ROC.




Fig. 1. Temperature-dependent MOKE hysteresis loops of 9.6 ML Ni/Cu₃Au (001) taken (a) in a longitudinal and (b) in a polar geometry.

temperature-dependent measurements of hysteresis loops by MOKE. Fig. 1 shows the temperature dependence of hysteresis loops for 9.6 ML Ni/Cu₃Au(001), taken in longitudinal and polar geometry. The coercivity decreases with increasing temperature, where coercivities in the longitudinal geometry are around 2 times higher than in the polar geometry. This indicates that the easy axis of magnetization is out of plane. We define T_C as the temperature at which we cannot see any hysteresis loops (coercivity $H_c=0$), determined by a linear fit of H_c as a function of T . The values of T_C of Ni/Cu₃Au(100) as a function of Ni thickness are shown in Fig. 2. Similar to Ni/Cu(100) [12–14], there is a spin reorientation transition (SRT) from in-plane to out-of-plane easy axis of magnetization with increasing Ni thickness also in Ni/Cu₃Au(001) [6,15]. We observe an SRT at around 8 ML Ni thickness in Ni/Cu₃Au(001). This higher SRT thickness compared to Ref. [15] could be due to a smoother growth of the Ni film and a concurrently later start of the onset of misfit dislocations.

We turn now to the change in T_C of the Ni layer while depositing NiMn on top. This change depends on the Ni/Mn ratio. We will first focus on Ni-rich Ni_xMn_{1-x} films.

3.1. Ni-rich Ni_xMn_{1-x} samples

Ni-rich Ni_xMn_{1-x} films were prepared at 68%, 71%, and 74% Ni concentrations. The bottom Ni layer thicknesses were 8.2, 9.6,




Fig. 2. Curie temperatures of Ni/Cu₃Au (001) as a function of Ni thickness. The vertical dashed line marks the SRT around 8 ML Ni thickness. The straight line is a linear fit from 7 ML to 10 ML used to correlate the Curie temperature variation in NiMn/Ni bilayers to a change of the effective Ni thickness.




Fig. 3. Ni Curie temperature as a function of the Ni_xMn_{1-x} thickness at different Ni concentrations in the Ni-rich regime. The scale bar at the right indicates the difference in Curie temperature corresponding to a 1 ML change of the effective Ni thickness estimated from the linear fit in Fig. 2.

and 12.6 ML. The dependence of T_C of these films on Ni_xMn_{1-x} thickness is shown in Fig. 3. For these Ni concentrations and Ni_xMn_{1-x} thicknesses the NiMn is paramagnetic at or above RT [16]. We observe that T_C increases slightly during the initial stages of growth of Ni_xMn_{1-x} on top of Ni, and partly relaxes back towards the initial value as the Ni_xMn_{1-x} thickness is further increased. We attribute this to a ferromagnetic polarization of Ni_xMn_{1-x} at the interface to Ni. This polarization increases the effective thickness of the Ni layer in the case of Ni-rich samples in the first few monolayers of Ni_xMn_{1-x} due to the fact that NiMn is paramagnetic at this concentration. We illustrate this in the sketches of Fig. 4. Upon deposition of Ni_xMn_{1-x}, the effective Ni thickness first increases, as shown in Fig. 4(b), where the entire Ni_xMn_{1-x} layer is ferromagnetically polarized. For larger Ni_xMn_{1-x} thicknesses, the polarization is saturated only at the interface, as shown in Fig. 4(c), which leads to a slight reduction in the effective thickness. A very similar behavior of induced ferromagnetic




Fig. 4. Schematic model for the Ni Curie temperature changes as a function of the Ni_xMn_{1-x} thickness in the Ni-rich regime. (a) Ni layer, (b) thin layer of Ni_xMn_{1-x} on top, and (c) thicker Ni_xMn_{1-x} layer.




Fig. 5. Ni Curie temperature as a function of the Ni_xMn_{1-x} thickness for different concentrations in the Mn-rich regime. The scale bar at the right indicates the difference in Curie temperature corresponding to a 1 ML change of the effective Ni thickness estimated from the linear fit in Fig. 2.

polarization has been observed by photoelectron emission microscopy (PEEM) in FeMn on Co [17]. Due to finite-size effects a change in the effective thickness of the Ni layer is accompanied by a respective change of T_C .

3.2. Mn-rich samples

In order to investigate the effect of Mn-rich Ni_xMn_{1-x} layers, we prepared films with 25%, 43%, and 48% Ni concentrations. The bottom Ni layer thicknesses were 7.9 and 10 ML. The top NiMn layer thicknesses were varied from 1.5 to around 10 ML. Fig. 5 shows the effect of the Ni_xMn_{1-x} layer on T_C of the Ni layer as a function of Ni_xMn_{1-x} thickness. The behavior found here is opposite to that in the Ni-rich concentration regime. T_C is clearly reduced with increasing Ni_xMn_{1-x} layer thickness. Discussing the effect again in terms of an effective Ni thickness, the deposition of Mn-rich Ni_xMn_{1-x} consequently leads to a reduction of the effective Ni thickness. Due to the tendency of Mn for antiferromagnetic exchange interaction, Mn-rich Ni_xMn_{1-x} films could lead to partial non-ferromagnetic behavior of some of the topmost Ni atoms of the Ni layer, possibly enhanced by intermixing at the interface. This is schematically depicted in Fig. 6. Upon initial deposition of Ni_xMn_{1-x}, the effective Ni thickness slightly decreases by enhanced fluctuations of topmost Ni atoms interacting with Mn of the Ni_xMn_{1-x} layer, as shown in Fig. 6(b). Since the




Fig. 6. Schematic model for the Ni Curie temperature changes as a function of the Ni_xMn_{1-x} thickness in the Mn-rich regime. (a) Ni layer, (b) thin layer of Ni_xMn_{1-x} on top, and (c) thicker layer of Ni_xMn_{1-x} with antiferromagnetic order.

antiferromagnetic ordering temperatures are higher for Mn-rich Ni_xMn_{1-x}, antiferromagnetic order sets in within the range of thicknesses probed here [6], and the Ni_xMn_{1-x} layer orders antiferromagnetically at higher thicknesses, as schematically shown in Fig. 6(c). We attribute the steps in the T_C vs. Ni_xMn_{1-x} thickness curves around 3–4 ML for Ni₂₅Mn₇₅ and around 7 ML for Ni₄₈Mn₅₂ to the onset of antiferromagnetic order in the respective Ni_xMn_{1-x} overlayer. A similar influence of antiferromagnetic order

on the transition between paramagnetic and ferromagnetic in an adjacent FM layer has been reported for FeMn/Co bilayers [10].

4. Conclusions

In conclusion, we have observed a change in the Curie temperature of a Ni layer on Cu₃Au(001) induced by the presence of a Ni_xMn_{1-x} overlayer and its dependence on the bottom Ni layer thickness, the ratio of NiMn composition, and NiMn thickness. Mn-rich overlayers cause a lowering of the Curie temperature, which is attributed to the tendency for antiferromagnetic order of Mn. In contrast, the Curie temperature slightly increases for Ni-rich overlayers, which is probably a consequence of induced ferromagnetic order in Ni_xMn_{1-x} close to the interface with Ni. All these interpretations are related to direct Ni–Ni, Ni–Mn, and Mn–Mn exchange interactions. A higher number of Ni–Ni interactions in the vicinity of the interface with the ferromagnetic Ni layer would increase the Curie temperature of the latter, while a higher number of Ni–Mn interactions decreases T_C .

Acknowledgments

Mustafa Erkovan would like to thank The Council of Higher Education Turkey (YÖK) for financial support during his stay in Berlin. Yasser Shokr would like to thank the DAAD for support.

References

- [1] S.A. Wolf, D.D. Awschalom, R.A. Buhrman, J.M. Daughton, S. von Molnár, M.L. Roukes, A.Y. Chtchelkanova, D.M. Treger, Spintronics: a spin-based electronics vision for the future, *Science* 294 (2001) 1488–1495.
- [2] W.H. Meiklejohn, C.P. Bean, New magnetic anisotropy, *Phys. Rev.* 105 (1957) 904–913.
- [3] J. Nogués, I.K. Schuller, Exchange bias, *J. Magn. Magn. Mater.* 192 (203) (1999) 203–232.
- [4] E. Demirci, M. Öztürk, E. Sınır, U. Ulucan, N. Akdoğan, O. Öztürk, M. Erkovan, Temperature-dependent exchange bias properties of polycrystalline Pt_xCo_{1-x}/CoO bilayers, *Thin Solid Films* 550 (2014) 595–601.
- [5] M.Y. Khan, C.-B. Wu, M. Erkovan, W. Kuch, Probing antiferromagnetism in NiMn/Ni(Co)/Cu₃Au(001) single-crystalline epitaxial thin films, *J. Appl. Phys.* 113 (2013) 023913-1–023913-7.
- [6] M.Y. Khan, Chii-Bin Wu, S.K. Kreft, W. Kuch, Concentration- and thickness-dependent magnetic properties of Ni_xMn_{100-x} in epitaxially grown Ni_xMn_{100-x}/Ni(Co)/Cu₃Au(001), *J. Phys.: Condens. Matter* 25 (2013) 386005-1–386005-11.
- [7] F. Offi, W. Kuch, J. Kirschner, Structural and magnetic properties of Fe_xMn_{1-x} thin films on Cu(001) and on Co/Cu(001), *Phys. Rev. B* 66 (2002) 064419-1–064419-10.
- [8] S.K. Mishra, F. Radu, S. Valencia, D. Schmitz, E. Schierle, H.A. Dürr, W. Eberhardt, Dual behavior of antiferromagnetic uncompensated spins in NiFe/IrMn exchange biased bilayers, *Phys. Rev. B* 81 (2010) 212404-1–212404-4.
- [9] Y. Wu, Nano spintronics for data storage, in: H.S. Nalwa (Ed.), *Encyclopedia for Nanoscience and Nanotechnology*, 7, American Scientific, Valencia, CA, 2003, p. 493.
- [10] C. Won, Y.Z. Wu, H.W. Zhao, A. Scholl, A. Doran, W. Kim, T.L. Owens, X.F. Jin, Z.Q. Qiu, Studies of FeMn/Co/Cu(001) films using photoemission electron microscopy and surface magneto-optic Kerr effect, *Phys. Rev. B* 71 (2005) 024406-1–024406-5.
- [11] W.A.A. Macedo, P.L. Gasteloi, M.D. Martins, W. Kuch, J. Miguel, M.Y. Khan, Growth, structure, and magnetic properties of epitaxial Ni_xMn_{100-x} single layers and Co/Ni_xMn_{100-x} bilayers on Cu₃Au(100), *Phys. Rev. B* 82 (2010) 134423-1–134423-8.
- [12] M. Farle, B. Mirwald-Schulz, A.N. Anisimov, W. Platow, K. Baberschke, Higher-order magnetic anisotropies and the nature of the spin-reorientation transition in face-centered-tetragonal Ni(001)/Cu(001), *Phys. Rev. B* 55 (1997) 3708–3715.
- [13] W. Kuch, J. Gilles, S.S. Kang, S. Imada, S. Suga, J. Kirschner, Magnetic circular dichroism microspectroscopy at the spin-reorientation transition in Ni(001) films, *Phys. Rev. B* 62 (2000) 3824–3833.
- [14] R. Vollmer, T. Gutjahr-Löser, J. Kirschner, S. van Dijken, B. Poelsema, Spin-reorientation transition in Ni films on Cu(001): the influence of H₂ adsorption, *Phys. Rev. B* 60 (1999) 6277–6280.
- [15] A. Braun, B. Feldmann, M. Wuttig, Strain-induced perpendicular magnetic anisotropy in ultrathin Ni films on Cu₃Au(001), *J. Magn. Magn. Mater.* 171 (1997) 16–28.
- [16] P. Pal, R. Banerjee, R. Banerjee, A. Mookerjee, G.C. Kaphle, P. Mitra, A. K. Majumdar, A.K. Nigam, Magnetic ordering in Ni-rich NiMn alloys around the multicritical point: experiment and theory, *Phys. Rev. B* 85 (2012) 174405-1–174405-12.
- [17] F. Offi, W. Kuch, L.I. Chelaru, K. Fukumoto, M. Kotsugi, J. Kirschner, Induced Fe and Mn magnetic moments in Co-FeMn bilayers on Cu(001), *Phys. Rev. B* 67 (2003) 094419-1–094419-8.